



# Standard Specification for Aluminum Bronze Rod, Bar, and Shapes<sup>1</sup>

This standard is issued under the fixed designation B 150/B 150M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

## 1. Scope\*

1.1 This specification establishes the requirements for aluminum bronze rod, bar, and shapes for Copper Alloys UNS Nos. C61300, C61400, C61900, C62300, C62400, C63000, C63020, C63200, C64200, and C64210.

NOTE 1—Product intended for hot forging is described in Specification B 124/B 124M.

NOTE 2—**Warning**—Mercury has been designated by EPA and many state agencies as a hazardous material that can cause central nervous system, kidney, and liver damage. Mercury, or its vapor, may be hazardous to health and corrosive to materials. Caution should be taken when handling mercury and mercury-containing products. See the applicable product Material Safety Data Sheet (MSDS) for details and EPA's website (<http://www.epa.gov/mercury/faq.htm>) for additional information. Users should be aware that selling mercury or mercury-containing products, or both, in your state may be prohibited by state law.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**B 124/B 124M** Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes

**B 154** Test Method for Mercurous Nitrate Test for Copper Alloys

**B 249/B 249M** Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings

**B 601** Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

**B 858** Test Method for Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys

**E 8** Test Methods for Tension Testing of Metallic Materials

**E 8M** Test Methods for Tension Testing of Metallic Materials [Metric]<sup>3</sup>

**E 18** Test Methods for Rockwell Hardness of Metallic Materials

**E 53** Test Method for Determination of Copper in Unalloyed Copper by Gravimetry

**E 62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)

**E 118** Test Methods for Chemical Analysis of Copper-Chromium Alloys

**E 478** Test Methods for Chemical Analysis of Copper Alloys

## 3. General Requirements

3.1 The following sections of Specification B 249/B 249M constitute a part of this specification:

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Workmanship, Finish, and Appearance,

3.1.4 Sampling,

3.1.5 Number of Tests and Retests,

3.1.6 Specimen Preparation,

3.1.7 Test Methods,

3.1.8 Significance of Numerical Limits,

3.1.9 Inspection,

3.1.10 Rejection and Rehearing,

3.1.11 Certification,

3.1.12 Mill Test Report,

3.1.13 Packaging and Package Marking, Preservation and Delivery, and

3.1.14 Supplementary Requirements.

<sup>3</sup> Withdrawn.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.02 on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved April 15, 2008. Published May 2008. Originally approved in 1941. Last previous edition approved in 2003 as B 150/B 150M – 03.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

TABLE 1 Chemical Requirements

Elements	Composition, %										
	C61300	C61400	C61900	C62300	Copper Alloy UNS No. C62400		C63000	C63020	C63200	C64200	C64210
Aluminum	6.0–7.5	6.0–8.0	8.5–10.0	8.5–10.0	10.0–11.5	9.0–11.0	10.0–11.0	8.7–9.5	6.3–7.6	6.3–7.0	
Copper, incl silver	remainder	remainder	remainder	remainder	remainder	remainder	74.5 min	remainder	remainder	remainder	
Iron	2.0–3.0	1.5–3.5	3.0–4.5	2.0–4.0	2.0–4.5	2.0–4.0	4.0–5.5	3.5–4.3 <sup>A</sup>	0.30 max	0.30 max	
Nickel, incl cobalt	0.15 max	...	...	1.0 max	...	4.0–5.5	4.2–6.0	4.0–4.8 <sup>A</sup>	0.25 max	0.25 max	
Manganese	0.20 max	1.0 max	...	0.50 max	0.30 max	1.5 max	1.5 max	1.2–2.0	0.10 max	0.10 max	
Silicon	0.10 max	...	...	0.25 max	0.25 max	0.25 max	...	0.10 max	1.5–2.2	1.5–2.0	
Tin	0.20–0.50	...	0.6 max	0.6 max	0.20 max	0.20 max	0.25 max	...	0.20 max	0.20 max	
Zinc, max	0.10 <sup>B</sup>	0.20	0.8	...	...	0.30	0.30	...	0.50	0.50	
Lead, max	0.01	0.01	0.02	...	...	...	0.03	0.02	0.05	0.05	
Arsenic, max	...	...	...	...	...	...	...	...	0.15	0.15	
Phosphorus, max	0.015	0.015	...	...	...	...	...	...	...	...	
Other named elements <sup>B</sup>							c				

<sup>A</sup> Iron content shall not exceed nickel content.

<sup>B</sup> When the product is for subsequent welding applications and is so specified by the purchaser, chromium shall be 0.05 % max, cadmium 0.05 % max, zirconium 0.05 % max, and zinc 0.05 % max.

<sup>C</sup> Chromium shall be 0.05 max and cobalt shall be 0.20 max.

3.2 In addition, when a section with a title identical to those referenced in 3.1, appears in this specification, it contains additional requirements that supplement those appearing in Specification B 249/B 249M.

#### 4. Ordering Information

4.1 Include the following information when placing orders for product under this specification, as applicable:

4.1.1 Specification designation and year of issue,

4.1.2 Copper alloy UNS No. (See Table 1),

4.1.3 Temper (see Temper section),

4.1.3.1 When Alloy UNS No. C63000 is specified, specify standard strength or high strength temper (See Table 2),

4.1.4 Product cross-section (for example round, hexagonal, square, and so forth),

4.1.5 Dimensions (diameter or distance between parallel surfaces and length) and permissible variations (Section 10),

4.1.5.1 When product of Copper Alloy UNS No. C63020 is specified, the tolerances for diameter, thickness, width, and length shall be part of the contract or purchase order and shall be agreed upon between the supplier and the purchaser.

4.1.5.2 Shapes—When product is shapes, the dimensional tolerances shall be as agreed upon between the manufacturer and the purchaser and shall be specified.

4.1.6 Quantity, total weight, footage, or number of pieces for each size.

4.1.7 If product is being purchased for agencies of the U.S. government.

4.2 The following options are available and should be specified at the time of placing the order when required:

4.2.1 If Copper Alloy C61300 material is intended for subsequent welding applications (See Note B, Table 2,

4.2.2 Certification,

4.2.3 Mill test reports,

4.2.4 Residual stress test (Performance Requirements section)

4.2.4.1 Ammonia Vapor Test or Mercurous Nitrate Test,

4.2.4.2 For Ammonia Vapor Test, pH value other than 10.

4.2.5 If piston finish or shafting is required, (Performance Requirements and Workmanship sections), and

4.2.6 When tensile test is required for alloys with hardness requirements in Table 3 (see 8.2.1).

#### 5. Materials and Manufacture

5.1 Manufacture:

5.1.1 Copper Alloy UNS C63020—Rod and Bar shall be heat-treated to 26 Rockwell hardness (C scale) (HRC) minimum as follows:

5.1.2 Heat to 1550°/1650°F [850/900°C] for 2 h minimum and quenched in water.

5.1.3 Temper at 900°/1000°F [480/540°C] for 2 h minimum and air cool to room temperature.

5.2 Copper Alloy UNS C63200—Rod and Bar shall be heat-treated as follows:

5.2.1 Heat to 1550°F [850°C] minimum for 1 h minimum at temperature and quench in water or other suitable medium,

5.2.2 Temper anneal at 1300 ± 25°F [700 ± 15°C] for 3 to 9 h at temperature as required to obtain desired mechanical properties, and

5.2.3 Heat treatment is not mandatory for sections that exceed 12 in. [300 mm] in diameter or thickness.

#### 6. Chemical Composition

6.1 The material shall conform by alloy to the chemical composition requirements in Table 1 for the copper alloy UNS designation specified in the ordering information.

6.2 For alloys in which copper is listed as “remainder,” copper is the difference between the sum of all elements determined and 100 %.

6.2.1 When all elements in Table 1 are determined, the sum of results shall be 99.5 % minimum for all alloys except C61300 which shall be 99.8 % min.

6.3 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and the purchaser, limits may be established and analysis required for unnamed elements.

TABLE 2 Tensile Requirements

Temper Designation		Diameter or Distance Between Parallel Surfaces, <sup>A</sup> in. [mm]	Tensile Strength, min ksi [MPa]	Yield Strength, min ksi [MPa], at 0.5 % Extension Under Load	Elongation in 4 × Diameter or Thickness of Specimen min, % <sup>B</sup>								
Code	Name												
Copper Alloy UNS No. C61300													
HR50	drawn and stress relieved	<i>rod (round only):</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2.0 [50] incl over 2 [50] to 3 [80], incl	80 [550] 75 [515] 72 [495] 70 [485]	50 [345] 45 [310] 40 [275] 35 [240]	30 30 30 30								
HR50	drawn and stress relieved	<i>rod (hexagonal and octagonal) and bar:</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl	80 [550] 75 [515] 70 [485]	40 [275] 35 [240] 32 [220]	30 30 30								
Copper Alloy UNS No. C61400													
HR50	drawn and stress relieved	<i>rod (round only):</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl	80 [550] 75 [515] 70 [485] 70 [485]	40 [275] 35 [240] 32 [220] 30 [205]	30 30 30 30								
Copper Alloy UNS No. C61900													
HR50	drawn and stress relieved	<i>rod (round only):</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl	90 [620] 88 [605] 85 [585] 78 [540]	50 [345] 44 [305] 40 [275] 37 [255]	15 15 20 25								
M20	as hot rolled	over 3 [80]	75 [515]	30 [205]	20								
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved	} <i>shapes, all sizes</i>	75 [515]	30 [205]	20								
Copper Alloy UNS No. C62300													
HR50	drawn and stress relieved					<i>rod (round only):</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl	90 [620] 88 [605] 84 [580] 76 [525]	50 [345] 44 [305] 40 [275] 37 [255]	12 15 15 20				
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved					} over 3 [80]	75 [515]	30 [205]	20				
HR50	drawn and stress relieved									<i>rod (hexagonal and octagonal) and bar:</i> 1 [25] and under over 1 [25] to 2 [50], incl	80 [550] 78 [540]	35 [240] 32 [220]	15 15
M20	as hot rolled									over 2 [50]	75 [515]	30 [205]	20
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved	} <i>shapes, all sizes</i>	75 [515]	30 [205]	20								
Copper Alloy UNS No. C62400													
HR50	drawn and stress relieved									<i>rod (round only):</i> ½ [12] and under over ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl	95 [655] 95 [655] 90 [620] 90 [620]	45 [310] 45 [310] 43 [295] 40 [275]	10 12 12 12
M20 M30	as hot rolled as hot extruded					over 3 [80] to 5 [125] incl	90 [620]	35 [240]	12				

TABLE 2 Continued

Code	Temper Designation Name	Diameter or Distance Between Parallel Surfaces, <sup>A</sup> in. [mm]	Tensile Strength, min ksi [MPa]	Yield Strength, min ksi [MPa], at 0.5 % Extension Under Load	Elongation in 4 × Diameter or Thickness of Specimen min, % <sup>B</sup>
O20 O25 O30	hot forged and annealed hot rolled and annealed hot extruded and annealed	<i>rod (hexagonal and octagonal) and bar:</i>			
		½ [12] to 5 [125], incl <i>shapes, all sizes</i>	90 [620] 90 [620]	35 [240] 35 [240]	12 12
TQ50	quench hardened and temper annealed	<i>rod (round only):</i> over 3 [80] to 5 [125], incl	95 [655]	45 [310]	10
Copper Alloy UNS No. C63000					
HR50	drawn and stress relieved	<i>1—standard strength</i> <i>rod:</i> ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl			
			100 [690] 90 [620] 85 [585]	50 [345] 45 [310] 42.5 [295]	5 6 10
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved	over 3 [80] to 4 [100], incl over 4 [100]	85 [585] 80 [550]	42.5 [295] 40 [275]	10 12
HR50	drawn and stress relieved	<i>bar:</i> ½ [12] to 1 [25], incl over 1 [25] to 2 [50], incl			
			100 [690] 90 [620]	50 [345] 45 [310]	5 6
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved	over 2 [50] to 4 [100], incl over 4 [100]	85 [585] 80 [550]	42.5 [295] 40 [275]	10 12
M20 M30 O20 O25 O30 HR50	as hot rolled as hot extruded hot forged and annealed hot rolled and annealed hot extruded and annealed drawn and stress relieved	<i>shapes, all sizes</i>			
			85 [585]	42.5 [295]	10
HR50	drawn and stress relieved	<i>2—high strength</i> <i>rod:</i> 1 [25] and under over 1 [25] to 2 [50], incl over 2 [50] to 3 [80], incl			
			110 [760] 110 [760] 105 [725]	68 [470] 60 [415] 55 [380]	10 10 10
TQ50 O32	quench hardened and temper annealed hot extruded and temper annealed	over 3 [80] to 5 [125], incl	100 [690]	50 [345]	10
Copper Alloy UNS No C63020					
TQ30	quenched hardened and tempered	<i>rod and bar:</i> up to 1 [25] incl over 1 [25] to 2 [50], incl over 2 [50] to 4 [100], incl			
			135 [930] 130 [890] 130 [890]	100 [690] <sup>C</sup> 95 [650] <sup>C</sup> 90 [620] <sup>C</sup>	6 6 6
Copper Alloy UNS No. C63200					
TQ50	quench hardened and temper annealed	<i>rod and bar:</i> up to 3 [80], incl over 3 [80] to 5 [125], incl			
TQ55	quench hardened, temper annealed, drawn, and stress relieved	over 5 [125] to 12 [300], incl <i>shapes, all sizes</i>	90 [620] 90 [620] 90 [620]	50 [345] 45 [310] 40 [275] 40 [275]	15 15 15 15
O20 O25	hot forged and annealed hot rolled and annealed	<i>bar and shapes</i> all sizes			
			90 [620]	40 [275]	15
Copper Alloy UNS Nos. C64200 and C64210					
HR50	drawn and stress relieved	<i>rod and bar:</i> ½ [12] and under			
			90 [620]	45 [310]	9

TABLE 2 Continued

Code	Temper Designation Name	Diameter or Distance Between Parallel Surfaces, <sup>A</sup> in. [mm]	Tensile Strength, min ksi [MPa]	Yield Strength, min ksi [MPa], at 0.5 % Extension Under Load	Elongation in 4 × Diameter or Thickness of Specimen min, % <sup>B</sup>
		over ½ [12] to 1 [25], incl	85 [585]	45 [310]	12
		over 1 [25] to 2 [50], incl	80 [550]	42 [290]	12
		over 2 [50] to 3 [80], incl	75 [515]	35 [240]	15
M10 M20 M30	as hot forged—air cooled as hot rolled as hot extruded	over 3 [80] to 4 [100] incl over 4 [100]	70 [485]	30 [205]	15
			70 [485]	25 [170]	15
M30	as hot extruded	shapes, all sizes	70 [485]	30 [205]	15

<sup>A</sup> For rectangular bar, the Distance Between Parallel Surfaces as used in this table refers to the thickness.

<sup>B</sup> Elongation values are based on 5.65 times the square root of the area for dimensions greater than 0.10 in. [2.5 mm]. In any case, a minimum gage length of 1 in. [25 mm] shall be used.

<sup>C</sup> Yield strength at 0.2 % offset.

TABLE 3 Rockwell Hardness Requirements<sup>A</sup>

Code	Temper Designation Name	Diameter or Distance Between Parallel Surfaces, in. [mm]	Rockwell Hardness Determined on the Cross Section Midway Between Surface and Center
Copper Alloy UNS No. C63020			
TQ30	Quench hardened and tempered	all sizes	C 26 min
Copper Alloys UNS Designations C64200 and C64210			
HR50	drawn and stress relieved	0.5 [12] to 1.0 [25], incl. over 1.0 [25] to 2.0 [50], incl. over 2.0 [50] to 3.0 [80], incl.	B 80 – 100 B 80 – 100 B 70 – 95
M30	as hot-extruded	over 3.0 [80] to 4.0 [100], incl. over 4.0 [100] shapes, all sizes	B 65 – 95 B 65 – 95 B 65–95

<sup>A</sup> Rockwell hardness requirements are not established for diameters less than 0.5 in. [12 mm].

## 7. Temper

7.1 The standard tempers for products described in this specification, and as defined in Classification B 601, are given in Tables 2 and 3.

- 7.1.1 Annealed tempers O20, O25, and O30.
- 7.1.2 Cold worked and stress relieved temper HR50.
- 7.1.3 As-manufactured tempers M10, M20, M30.
- 7.1.4 Heat treated tempers O32, TQ30, TQ50 and TQ55.

NOTE 3—UNS No. C63000 has two available strength levels available in rod, standard strength and high strength.

## 8. Mechanical Property Requirements

8.1 Product furnished under this specification shall conform to the mechanical property requirements prescribed in Table 2 and Table 3 for the Copper Alloy UNS No. designation specified in the ordering information.

8.2 Rockwell Hardness Requirement—For the alloys and tempers listed in Table 3, product 0.5 in. [12 mm] and over in diameter or distance between parallel surfaces shall conform with the requirements prescribed in Table 3, when tested in accordance with Test Methods E 18.

8.2.1 For Copper Alloys UNS Nos. C64200 and C64210 in tempers listed in Table 3, Rockwell hardness shall be the basis of acceptance or rejection for mechanical properties except when the tensile test is specified in the contract or purchase order.

8.3 Tensile Strength Requirements—Product furnished under this specification shall conform to the tensile requirements in Table 2 when tested in accordance with Test Methods E 8 or E 8M.

## 9. Performance Requirements

### 9.1 Residual Stress Test:

9.1.1 When specified in the contract or purchase order, the product shall be tested for residual stress according to the requirements of Test Method B 154 or Test Method B 858, and show no signs of cracking.

**Warning**—Mercury is a definite health hazard. With the Mercurous Nitrate Test, equipment for the detection and removal of mercury vapor produced in volatilization, and the use of protective gloves is recommended.

9.1.2 When the ammonia vapor test is used, the test pH value appropriate for the intended application shall be 10 unless otherwise specified by the purchaser.

NOTE 4—A residual stress test provides information about the adequacy of the stress relief of the material. Bar straightening is a method of mechanical stress relief. Stress relief annealing is a method of thermal stress relief.

9.2 Piston Finish—When specified, round rod over 0.5 in. [12 mm] in diameter shall be furnished piston finished. Refer to Specification B 249/B 249M.

## 10. Dimensions and Permissible Variations

10.1 The dimensions and tolerances for product described by this specification shall be as specified in Specification B 249/B 249M with particular reference to the following tables and related paragraphs:

10.1.1 *Diameter or Distance between Parallel Surfaces, Rod (Round, Hexagonal, Octagonal):*

10.1.1.1 *Rod: Cold Drawn Tempers*—Refer to applicable Table 2 on Tolerances for Diameter or Distances Between Parallel Surfaces of Cold-Drawn Rod.

10.1.1.2 *Rod, M30, O30, and O32 tempers*—Refer to Table 4 on Tolerances for Diameter or Distance Between Parallel Surfaces of As-Extruded Rod and Bar.

10.1.1.3 *Round Rod, M20 temper*—Refer to Table 6 on Diameter Tolerances for Hot-Rolled Round Rod.

10.1.1.4 *Piston Finish Rod*—Refer to Table 3 on Diameter Tolerances for Piston-Finished Rod.

10.1.2 *Distance between Parallel Surfaces, Bar (Rectangular and Square):*

10.1.2.1 *Bar, Drawn Tempers*—Refer to Table 9 on Thickness Tolerances for Rectangular and Square Bar, and Table 11 on Width Tolerances for Rectangular Bar.

10.1.2.2 *Bar, M30, O30, and O32 Tempers*—Refer to Table 4 on Tolerances for Diameter or Distance Between Parallel Surfaces of As-Extruded Rod and Bar.

10.1.3 *Length of Rod, Bar and Shapes*—Refer to Table 13 on Length Tolerances for Rod, Bar, and Shapes, and Table 15 on Schedule of Lengths (Specific and Stock) with Ends for Rod and Bar.

10.1.4 *Straightness:*

10.1.4.1 *Rod and Bar*—Refer to Table 16 on Straightness Tolerances for Rod, Bar, and Shapes.

10.1.4.2 *Shafting Rod*—Refer to Table 17 on Straightness Tolerances for Shafting.

10.1.4.3 *Rod, Bar and Shapes of M20, M30, O30, and O32 Temper*—They shall be of sufficient straightness to meet the requirements of the intended application.

10.1.5 *Edge Contours*—Refer to section entitled, “Edge Contours.”

10.2 *Shapes*—The cross section dimensional tolerances for shapes shall be as agreed upon between the manufacturer and the purchaser.

## 11. Workmanship, Finish and Appearance

11.1 When specified in the contract or purchase order, round rod over ½ in. [12 mm] in diameter shall be furnished as piston finish rod or shafting.

## 12. Test Methods

12.1 *Chemical Analysis:*

12.1.1 In cases of disagreement, determine the composition using the following methods:

Element	ASTM Test Methods
Aluminum	E 478, Titrimetric
Arsenic	E 62
Copper	E 478
Iron	E 478, Photometric
Lead	E 478, Atomic absorption
Manganese	E 62
Nickel	E 478, Photometric
Phosphorous	E 62
Silicon	E 62
Tin	E 478, Photometric
Zinc	E 478, Atomic absorption
Cadmium	E 53
Chromium	E 118

12.1.2 Test methods to be followed for the determination of elements resulting from contractual or purchase order agreement shall be as agreed upon between the manufacturer or supplier and the purchaser.

## 13. Keywords

13.1 aluminum bronze bar; aluminum bronze rod; aluminum bronze shapes; UNS Alloy No. C61300; UNS Alloy No. C61400; UNS Alloy No. C61900; UNS Alloy No. C62300; UNS Alloy No. C62400; UNS Alloy No. C63000; UNS Alloy No. C63020; UNS Alloy No. C63200; UNS Alloy No. C64200; UNS Alloy No. C64210

## SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B 150/B 150M-03) that may impact the use of this standard. (Approved April 15, 2008.)

(1) Various sections were editorially revised to conform to the latest revision of Standard Guide B 950.

(2) Added existing Hardness requirements for C63020 to Table 3.



*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).*